

Ultrabond ECO 399

Heavy-Duty, Pressure-Sensitive, Multi-Flooring
Adhesive



DESCRIPTION

Ultrabond ECO® 399 is a high-moisture-resistant, heavy-rolling-load-resistant, aggressive, pressure-sensitive adhesive with enhanced dimensional control properties designed to install a wide variety of resilient flooring types. *Ultrabond ECO* 399 can also be used for flash-coving installations using traditional installation methods.

FEATURES AND BENEFITS

- Resistant to heavy rolling loads
- Minimizes gaps in luxury vinyl tile and plank
- Resistant to high moisture
- Allows up to 6 hours of working time

WHERE TO USE

- Approved for use with vinyl composition tile (VCT), luxury vinyl tile, luxury vinyl plank, vinyl enhanced tile, quartz tile, bio-based tile, fiberglass-reinforced vinyl sheet flooring, solid vinyl sheet flooring, reground rubber underlayment, rubber sheet and tile flooring, cork underlayment, and vinyl-backed and polyolefin-backed carpet tile

LIMITATIONS

- Do not install over substrates containing asbestos.
- For interior installations only
- Install flooring only in areas recommended by the flooring manufacturer.
- Do not install into wet adhesive over nonporous substrates.
- Do not apply over any adhesive residues, including cutback adhesive.
- Do not use to install luxury vinyl tile or luxury vinyl plank with known dimensional stability issues.
- Do not install when the moisture vapor emission rate (MVER) exceeds 15 lbs. per 1,000 sq. ft. (6.80 kg per 92.9 m²) per 24 hours, when using the anhydrous calcium chloride test (per ASTM F1869).
- Do not install when the relative humidity (RH) of the concrete slab exceeds 99% (per ASTM F2170).
- Do not install in areas with known moisture problems.
- Use only when the substrate temperature is between 50°F and 90°F (10°C and 32°C).
- Do not install unless the surface temperature of the substrate is 5 degrees Fahrenheit (2.8 degrees Celsius) above the dew point.
- Do not install when the pH is 12 or greater.

SUITABLE SUBSTRATES

- Concrete (at least 28 days old, installed per ASTM F710)
- Cement terrazzo
- Exterior-grade plywood and other approved wood substrates (per the flooring manufacturer's recommendations)
- Cement-based self-leveling underlayments and patching compounds
- Embossing levelers applied over existing and fully bonded ceramic tile and sheet vinyl
- A single layer of fully bonded VCT
- Properly primed gypsum underlayments that meet the requirements for compressive strength according to ASTM F2419
- Radiant-heat systems that have been properly installed and operating at a surface temperature no higher than 85°F (29°C)
- Properly installed and sound MAPEI epoxy moisture barriers

Consult MAPEI's Technical Services Department for installation recommendations regarding substrates and conditions not listed.

SURFACE PREPARATION

- All substrates must be structurally sound, dry, solid and stable.
- The substrate should be clean and free of dust, dirt, oil, grease, paint, curing agents, concrete sealers, loosely bonded toppings, loose particles, and any other substance or condition that may affect the overall performance of the product.
- Substrates must be flat to 3/16" in a 10-ft. span (4.5 mm in a 3.05-m span).

See the “Surface preparation requirements” reference guide in the Floor Covering Installation Systems section of MAPEI’s Website.

MIXING

Before product use, take appropriate safety precautions. Refer to the Safety Data Sheet for details.

- Ready to use, with no mixing necessary

PRODUCT APPLICATION

Refer to the flooring manufacturer’s guidelines for acclimation requirements and complete installation instructions. Read all installation instructions thoroughly before installation.

1. Select the appropriately notched trowel (see the “Approximate Coverage” chart below) and spread the adhesive evenly over the subfloor, keeping the trowel at a 45-degree angle to the subfloor.
2. On nonporous substrates, allow adhesive to remain open for 30 to 60 minutes or until it is dry to the touch, and then place the flooring.
3. On porous substrates, flooring can be installed into semi-wet adhesive. Or allow the adhesive to remain open for 30 to 60 minutes until it is dry and does not transfer to the finger when touched.
4. Only apply as much adhesive as can be installed within 6 hours. Protect the open adhesive from dust and debris, which will inhibit proper bond and decrease tack.
5. Roll flooring using a 75-lb. (34.0-kg) or 100-lb. (45.4-kg) roller.

CLEANUP

- Use water to clean adhesive smudges from the flooring surface and tools while the adhesive is fresh/wet.

PROTECTION

- Protect the finished installation from light traffic for at least 6 hours and from heavy traffic for at least 12 hours.
- Building owners should become aware of the flooring manufacturer’s guidelines for climate-control settings (temperature and humidity). These conditions must be monitored and kept constant to ensure the overall performance and long-term success of the installation.

Product Performance Properties

Laboratory Tests	Results
Solids content	50% to 55%
Density	8.3 lbs. per U.S. gal. (0.99 g per mL)
Flash point (Tag)	> 201°F (94°C)
VOC content (SCAQMD Rule 1168)	< 50 g per L
Typical VOC content per SCAQMD Rule 1168 testing methods	32 g per L

Shelf Life and Product Characteristics

Shelf life	2 years when stored in original, unopened packaging at 73°F (23°C)
Storage conditions	50°F to 90°F (10°C to 32°C)
Adhesive type	Acrylic latex
Consistency	Smooth paste
Color	Off-white

Protect containers from freezing in transit and storage. If frozen, material should not be stirred until it has completely thawed. Provide for heated storage on site and deliver all materials at least 24 hours before work begins.

Application Properties

at 73°F (23°C) and 50% RH

Working time*	< 6 hours

** Working time may vary based on temperature, humidity, substrate porosity, trowel size and jobsite conditions.*

Packaging

Size
Pail: 1 U.S. gal. (3.79 L)
Pail: 4 U.S. gals. (15.1 L)

Approximate Coverage**

per 4 U.S. gals. (15.1 L)

Flooring Type	Typical Application Tool	Coverage
Luxury vinyl tile/plank, bio-based tile, vinyl enhanced tile, VCT, solid vinyl sheet flooring and rubber sheet/tile on porous substrates	1/16" x 1/16" x 1/16" (1.5 x 1.5 x 1.5 mm), square-notch trowel	500 to 740 sq. ft. (46.5 to 68.7 m ²)
Luxury vinyl tile/plank, bio-based tile, vinyl enhanced tile, VCT, solid vinyl sheet flooring and rubber sheet/tile on nonporous substrates	1/16" x 1/32" x 1/32" (1.5 x 1 x 1 mm), U-notch trowel	740 to 980 sq. ft. (68.7 to 91.0 m ²)
Vinyl-backed and polyolefin-backed carpet tile, and fiberglass-reinforced sheet vinyl	1/16" x 1/32" x 1/32" (1.5 x 1 x 1 mm), U-notch trowel	740 to 980 sq. ft. (68.7 to 91.0 m ²)
	1/4" (6 mm) nap roller	1,000 to 1,400 sq. ft. (92.9 to 130 m ²)

**Trowel dimensions are depth/width/space. Coverage shown is for estimating purposes only. Actual jobsite coverage may vary according to substrate conditions, type of trowel used and setting practices.

ADDITIONAL INFORMATION

Refer to the Safety Data Sheet (SDS) for specific data related to health and safety as well as product handling.

For information on MAPEI's commitment to sustainability and transparency, as well as how MAPEI products may contribute to green building standards and certification systems, contact sustainability-durabilite@mapei.com.

WARNING

The test results shown in the TECHNICAL DATA table were obtained in compliance with test methods and curing cycles, if applicable, defined in the industry standards referenced on the Technical Data Sheet. Please note that the use of test procedures or methods other than those indicated in the table could lead to different values and that, in such cases, any liability of our company is excluded.

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement nor replace requirements per the TDS in effect at the time of the MAPEI product installation. For the most up-to-date TDS and warranty information, please visit our website at www.mapei.com. **ANY ALTERATIONS TO THE WORDING OR REQUIREMENTS CONTAINED IN OR DERIVED FROM THIS TDS SHALL VOID ALL RELATED MAPEI WARRANTIES.**

Before using, the user must determine the suitability of our products for the intended use, and the user alone assumes all risks and liability. **ANY CLAIM SHALL BE DEEMED WAIVED UNLESS MADE IN WRITING TO US WITHIN FIFTEEN (15) DAYS FROM DATE IT WAS, OR REASONABLY SHOULD HAVE BEEN, DISCOVERED.**

CONTACT INFORMATION

MAPEI Headquarters of North America

1144 East Newport Center Drive
Deerfield Beach, Florida 33442
1-888-US-MAPEI (1-888-876-2734) / (954) 246-8888

Technical Services

U.S. and Puerto Rico:

Flooring: 1-800-992-6273

Concrete and heavy construction: 1-888-365-0614

Canada:

1-800-361-9309

Customer Service

1-800-42-MAPEI (1-800-426-2734)

Edition Date: October 7, 2025 MK 3000402 (25-2025)

For the most current product data and BEST-BACKEDSM warranty information, visit www.mapei.com.

All Rights Reserved. © 2025 MAPEI Corporation.

