

## Traditional Wall Base

## Product Specification

### 1. PROPRIETARY PRODUCT/MANUFACTURER

#### 1.1. Proprietary Product: Thermoplastic Wall Base

#### 1.2. Manufacturer:

Tarkett North America                      Phone:     (800) 899-8916  
30000 Aurora Rd.                                (440) 543-8916  
Solon, Ohio 44139  
Web: www.tarkett.com

#### 1.3. Proprietary Product Description:

1.3.1. **Construction:** Tarkett Traditional Wall Base is manufactured from a proprietary rubber and vinyl formulation designed specifically to meet the performance and dimensional requirements of ASTM F-1861, Type TV (Thermoplastic Vinyl) and TP (Thermoplastic Rubber), Group 1 (solid), Style A and B, Standard Specification for Resilient Wall Base.

#### 1.3.2. Styles/Physical Characteristics:

##### Rubber Wall Base

- **Traditional:** DC-XX with toe (coved) or DCT-XX for toeless (straight), 0.125" (3.17 mm) thickness, 2-1/2" (6.35 cm), 4" (10.16 cm), 4 1/2" (11.4 cm) or 6" (15.24 cm) height

Available in 4' (1.22 m) straight lengths and 120' (36.58 m) coiled lengths. The 6" (15.24 cm) high profile available in 4' (1.22 m) straight lengths and 100' (30.48 m) coiled lengths

- **Wall Art:** WA-XX w/toe (coved), 0.125" (3.17 mm) thickness, 4" (10.16 cm) height

Available in 4' (1.22 m) straight lengths only

- **Inside and Outside Corners** available with 4" (10.16 cm) returns packaged 25 per carton, add LIC (Inside corners) or LOC (Outside corners)

##### Vinyl Wall Base

- **Traditional:** CB-XX with toe (coved) or CBT-XX toeless (straight), 0.125" (3.17 mm) or 0.080" thickness, 2-1/2" (6.35 cm), 4" (10.16 cm), or 6" (15.24 cm) height

Cartons size: Available in 4' (1.22 m) straight lengths and 120' (36.58 m) coiled lengths. The 6" (15.24 cm) high profile available in 4' (1.22 m) straight lengths and 100' (30.48 m) coiled lengths

- **Inside and Outside Corners** available with 4" (10.16 cm) returns packaged 25 per carton, add LIC (Inside corners) or LOC (Outside corners)

### 2. PRODUCT PERFORMANCE AND TECHNICAL DATA

2.1. Meets or exceeds the performance requirements for resistance to heat/light aging, chemicals, and dimensional stability when tested to the methods, as described, in ASTM F-1861.

2.2. **Flexibility:** Will not crack, break, or show any signs of fatigue when bent around a 1/4" (6.4 mm) diameter cylinder.

2.3. **Chemical resistance** (ASTM F 925): Passes – 5% acetic acid, 70% isopropyl alcohol, mineral oil, 5% sodium hydroxide solution, 5% hydrochloric acid solution, 5% sulfuric acid solution, 5% household ammonia solution, and 5.25% household bleach solution

2.4. **Resistance to light** (ASTM F 1515):  $\Delta E < 8$

#### 2.5. Fire Resistance:

##### Vinyl Wall Base

ASTM E 648 (NFPA 253): Critical Radiant Flux – Class I

##### Rubber Wall Base

ASTM E 648 (NFPA 253): Critical Radiant Flux – Class I

#### 2.6. CAN/ULC-S102.2:

##### Vinyl Wall Base

FSR 140 / SDV 330

##### Rubber Wall Base

FSR 165 / SDV 345

### 3. AVAILABILITY AND COST

For availability and cost contact authorized Tarkett distributors nationwide.

### 4. INSTALLATION

4.1. See Tarkett wall base installation instructions for complete details.

#### 4.2. Adhesives:

- **Tarkett 960 Cove Base Adhesive** (Porous surfaces):

Application: 1/8" x 1/8" x 1/8" square notched trowel

Approximate coverage:

2 1/2" high – 300 to 350 linear feet/gallon

4" high – 200 to 250 linear feet/gallon

6" high – 100 to 150 linear feet/gallon

- **Tarkett 946 Premium Contact Adhesive** (Non-porous surfaces)

Application: Brush or roller

Approximate coverage:

1 Quart (0.95 liters) – 24 to 36 sq. ft.

1 Gallon (3.79 liters) – 100 to 150 sq. ft.

### Tarkett North America

Technical Services Department

30000 Aurora Road

Solon, Ohio 44139

800.899.8916

info@tarkettna.com

[www.tarkett.com](http://www.tarkett.com)

**5. MAINTENANCE**

72 hours after installation is completed, initial maintenance procedures must be implemented in accordance with manufacturer's requirements. Refer to the Rubber Vinyl Wallbase Installation & Maintenance instructions for full details.

**6. TECHNICAL SERVICES**

Visit us on the web at [www.tarkett.com](http://www.tarkett.com)

Contact Technical Support at (800) 899-8916 or E-mail:

[Resilient.TechnicalSupport@Tarkett.com](mailto:Resilient.TechnicalSupport@Tarkett.com)

**Samples:** Submittal samples for verification and approval available upon request from Tarkett. Samples shall be submitted in compliance with the requirements of the contract documents. Accepted and approved samples shall constitute the standard materials which represent materials installed on the project.

**7. LIMITED WARRANTY**

Limited 2 year warranty. For complete details, contact Tarkett or an authorized Tarkett distributor

---

**Tarkett North America**

Technical Services Department

30000 Aurora Road

Solon, Ohio 44139

800.899.8916

[info@tarkettna.com](mailto:info@tarkettna.com)

[www.tarkett.com](http://www.tarkett.com)